

STOKVIS TRADING BV

Service	Service conditions		Recommendable material	
	Temperature		Studbolt	Nut
	°F	°C	Astm	Astm
High pressure and high temperature	32 ~ 1148	0 ~ 620	A193 B5	A194 Gr.3
	32 ~ 896	0 ~ 480	A193 B6	A194 Gr.6
	-58 ~ 842	-50 ~ 450	A193 B7	A194 Gr.2H
	-58 ~ 1022	-50 ~ 550	A193 B16	A194 Gr.4 or 7
	~ 1292	~ 700	A453 660	A194 Gr.8T or 8C
High corrosive and high temperature	1104 ~ 1472	540 ~ 800	A193 B8	A194 Gr.8
	1104 ~ 1472	540 ~ 800	A193 B8M	A194 Gr.8M
	1104 ~ 1472	540 ~ 800	A193 B8T	A194 Gr.8T
High pressure and low temperature	-148 ~ -58	-100 ~ -50	A320 L7	A194 Gr.4 or 7
	-148 ~ -58	-100 ~ -50	A320 L43	A194 Gr.7
Low temperature	-418 ~ -148	-250 ~ -100	A320 B8	A194 Gr.8
	-328 ~ -148	-200 ~ -100	A320 B8M	A194 Gr.8M
	-328 ~ -148	-200 ~ -100	A320 B8T	A194 Gr.8T